

Product Technology Service

Report No.:TX2013060801

Page 1 of 3

Test Report

Testing institute : Product Technology Service (Ningbo) Co., Ltd.
6&7F, 59#, Huayu Road,
Yinzhou District, Ningbo 315192 P.R.China

Applicant : Triumphchi Industry & Trading Co., Ltd
/ Yiwu Really Textiles Co.,Ltd

Buyer : DIAMOND PLASTIC CO(PVT)LTD

Product name : NON WOVEN FARIC

Colour : ORANGE

Material : Polypropylene


Sample receive date : Jun.08,2013


Completes date : Jun.13,2013

Testing location : Product Technology Service (Ningbo) Co., Ltd.

Test specification(s) : For compliance with the Flammability
test requirements of Title 16, Code of Federal Regulations,
Chapter II – Consumer Products Safety Commission of U.S.A

Conclusion : Pass


Originator:
Della Wang


Verifier:
Jason Li


Authorizer:
Waterson Ltd

Ningbo, Jun.13,2013

The test results exclusively refer to the samples examined. This report shall not be reproduced except in full without written approval and does not authorize the use of Product Technology Service (Ningbo) Co., Ltd. label. The report is invalid without signature and seal of Product Technology Service (Ningbo) Co., Ltd.

Product Technology Service (Ningbo) Co., Ltd.
6 & 7F, Huayu Road, 59#
Yinzhou District
Ningbo 315192 P.R.China
TEL: 86-574-83036506
FAX: 86-574-83036508
E-mail: info@pls-lab.com

Tel. 86-574-83036506
Fax: 86-574-83036508
P.R. 315192
E-mail: info@pls-lab.com

宁波中检检测技术有限公司
浙江省宁波市
鄞州中心区华裕路
69号6楼
[Ningbo Zhongjian Testing Technology Co., Ltd.]

电话: 86-574-83036506
传真: 86-574-83036508
邮编: 315192
E-mail: info@pls-lab.com

Product Technology Service

Report No.:TX2013060801

Page 2 of 3

Test specification(s) : For compliance with the Flammability test requirements of Title 16, Code of Federal Regulations, Chapter II – Consumer Products Safety Commission of U.S.A.

Results :

US CPSC

1. Flammability Test

Flammability Test on Textile Materials

Samples		Burning Time (second)													
		As Received							After Washing						
1	Non woven faric	1	2	3	4	5	Ave.	Class	1	2	3	4	5	Ave.	Class
		DNI	DNI	DNI	DNI	DNI	DNI	I	DNI	DNI	DNI	DNI	DNI	DNI	I
		6	7	8	9	10			6	7	8	9	10		
		DNI	DNI	DNI	DNI	DNI			DNI	DNI	DNI	DNI	DNI		

Remark:

DNI = Did Not Ignite

Classification:	Class I (Acceptable) Normal Flammability	Class II (Acceptable) Intermediate Flammability	Class III (Reject) Rapid and Intense Flammability
Plain Surface Textile Fabrics	$\geq 3\frac{1}{2}$ sec	-----	$< 3\frac{1}{2}$ sec
Raised Surface Textile Fabric	> 7 sec. ; or 0 ~ 7 sec with no base burns (SFBB)	4 ~ 7 s with base burn (SFBB)	< 4 sec. with base burn (SFBB)

N.B. : Only applicable clauses were shown.

Sample photo(s),see annex 1

---END---

Product Technology Service

Report No.: TX2013060801

ANNEX 1

Sample photos, Consists of 1 page



Page 3 of 3



NON WOVEN FARIC

Product Technology Service (Ningbo) Co., Ltd.

6 & 7F, Huayu Road, 59#
Yinzhou District

Ningbo 315192 P.R.China

<http://www.pts-lab.com>

NO.: JC-TS-R003-02

Tel: 86-574-83036506

Fax: 86-574-83036506

P.R.: 315192

E-mail: info@pts-lab.com

宁波中普检测技术服务有限公司

浙江省宁波市

鄞州中心区 华裕路

69 号 6 & 7 楼

<http://www.pts-lab.com>

电话: 86-574-83036506

传真: 86-574-83036506

邮编: 315192

邮箱: info@pts-lab.com